Shiley School of Engineering, University of Portland EGR 221 - Materials Science, Exam 2 (closed book, closed notes, NO calculator) October 13, 2015. Dr. Ken Lulay

NAME: SOLUTION
1) {5 pts} Answer true (T) or false (F):
A. Poisson's ratio is: $-\varepsilon_{tr}/\varepsilon_{ax}$, where ε_{tr} is the transvers strain and ε_{ax} is the axial strain T
B. Diffusion rate is affected by the temperature (T) F Generally
C. In order for two different metals to be completely soluble in each other, they must have different crystal structures from each other. T (F) MUST HAVE SAME
D. Toughness is defined as the amount of strain in a material before fracturing. T F Amount of every
E. Diffusion rate (aka flux) is linearly proportional to the concentration gradient. T
2) {15 pts} Fill in the blanks with the correct terminology: $F = -D \partial_x^2 \partial_x$
A. The material property that characterizes a material's ability to resist penetration of a sharp
object, or in other words, ability to withstand local deformation by surface indentation is
known as: hardness.
B. The equation, E=σ/ε, is known as: Hooke's Law (Young's mod, E, is a maternal)
C. A solid solution wherein relatively small solute atoms occupy the "open space" between the proper solvent atoms is referred to as: intershifted impossity of intershal solid solved. D. The equation for elongation (%EL) is: %EL = (lfract -lo/lo) ×100%
D. The equation for elongation (%EL) is: %EL = () fract - 10 / x 100%
E. The material property defined as the maximum stress on a stress-strain diagram is known as: tensile strength (or ultimate trensile strongth)
3) {5 pts} Multiple Choice. Pick the single answer in each question that is most correct. A. In aluminum, self-diffusion:
a) will result in change of the of composition in the aluminum. b) atoms of aluminum will migrate through the aluminum. c) will change the crystal structure of the aluminum. d) self-diffusion cannot happen in aluminum.

B. An alloy is a:

a) pure metal

b) mixture of a metal and another element (metal or non-metal)
c) mixture of a metal and another metal only
d) mixture of a metal and non-metal only

4) {5 pts} Will carbon likely diffuse more quickly in iron at 915°C or at 910°C? F	Remember that
iron is Face Centered Cubic (FCC) above 912°C and Body Centered Cubic (BCC)	below 912°C.
Briefly justify/explain your answer.	

FCC	io mos	o tig	htly P	acked	(great	her APF)	; therefor
has	less '	10pen	Space	" than	BCC	. The	,
open	Spau	· in	BCC	a//wws	i for	easter	faster
diff	, 15:00					<i>(</i>	
		٠,٠	faster	at 910	2°C	Hum 915	~ ~ _

5) {30 pts} A cylindrical bar is loaded in tension as shown. The original gage length of the bar is 2.0000 inches and the original diameter is 0.5050 inches. When a 15,000 pound load is applied the gage length becomes 2.0050 inches and the diameter becomes 0.5045 inches. Determine the following – assume the 15,000 pound load is applied for all questions. STATE ALL ASSUMPTIONS, SHOW EQUATIONS IN VARIABLE FORM FIRST, THEN INCLUDE APPROPRIATE NUMBERS. YOU DO NOT NEED TO CALCULATE THE ANSWERS.

a) What is the normal stress along the axis of the bar (σ_{axial}) ?

$$\frac{6}{4} = \frac{15,000}{4}$$
 $A = \frac{17}{4} d^2 = 0.505 \text{ in}$

b) What is the strain along the axis of the $bar(\varepsilon_{axial})$?

c) What is the stress perpendicular to the axis of the bar $(\sigma_{transverse})$?

d) What is the strain perpendicular to the axis of the bar (\(\epsilon_{transverse}\))?

$$E_1 = \frac{d-d_0}{d} = \frac{0.5045^{\circ} - 0.5050^{\circ}}{0.5050^{\circ}}$$

f) What is Young's modulus (aka modulus of elasticity) of the material? State assumptions.